

COATED FABRIC PROPERTIES	TEST METHOD	REQUIREMENTS
Color	Visual	White
Width (trimmed)	ASTM D 751-89, sec. 8	60"
Weight	ASTM D 751-89, sec. 10.2	16.0 ± 2.0 oz/yd ²
Gauge	ASTM D 751-89, sec. 9	Record Only
Adhesion – Side 1	Fed. Std 191A, Method 5970	8.0 lbs/in. min.
Adhesion – Side 2	Fed. Std 191A, Method 5970	8.0 lbs/in. min.
Tongue Tear – Warp	ASTM D 751-89, sec. 22	50.0 lbs. min.
Tongue Tear – Fill	ASTM D 751-89, sec. 22	50.0 lbs. min.
Grab Tensile – Warp	ASTM D 751-89, sec. 11	400.0 lbs. min.
Grab Tensile – Fill	ASTM D 751-89, sec. 11	400.0 lbs. min.
DuPont Scrubs – Side 1	Trelleborg Test Method	3000 cycles min.
DuPont Scrubs – Side 2	Trelleborg Test Method	3000 cycles min.
State of Cure – Side 1	Trelleborg Test Method	Pass
State of Cure – Side 2	Trelleborg Test Method	Pass
Color Check	Trelleborg Test Method	Pass

Original Date: 08/10

Data presented are averaged results and should not be construed as specification limits.

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Reeves Brothers, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.
 790 Reeves Street
 Spartanburg, SC - 29301
 1-800-635-9350 - fax (864) 595-2211

