

Due to the technical limitations of characteristics and colors screen may be slightly different than the actual

TEXTILENE® 95 is a durable synthetic fabric made of PVC coated polyester. Designed to reduce heat transfer and solar glare, our fabric can lower overall energy cost and protect indoor furnishings. Flame and fade resistant, it is an excellent choice for a variety of indoor or outdoor uses.

*Custom colors and widths available. Minimum order of 1000 yds. Upcharges may apply. ** Available in 33.3 lyd rolls.

1-800-633-7550 | twitchellcorp.com Twitchell Technical Products, LLC

Specifications

REACH Compliant - Regulated by Registration, Evaluation, Authorization and Restriction of Chemicals. REACH places greater responsibility on industry to manage the risks that chemicals may pose to human health and the environment.







Children's Toy Act - Does not contain harmful phthalates listed under Section 108 of the Consumer Product Safety Improvement Act of 2008 (CPSIA).

Fire Classification - Passes California U.S. Title 19 (small scale), NFPA701-2015 TM#1 (small scale), NFPA 101 (Class A Rating), UBC (Class 1), BS 5867 2008 Part 2 Type B Performance, NFPA 701 TM #2 (large scale), and CAN/ULC-S 109-03 (large and small

Environmental Certification - GREENGUARD gold certified. Acceptable for use







in environments such as schools and healthcare facilities. Complies with requirements of the State of California's Department of Public Health "Standard Method for Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources Using Environmental Chambers, Version 1.1 (2010)" (also known as California Section 01350). RoHS Compliant - Free of Lead (Pb), Cadmium (Cd), Mercury (Hg), Hexavalent





chromium (Hex-Cr), Polybrominated biphenyls (PBB), and Polybrominated diphenyl ethers (PBDE).

Bacteria and Fungal Resistance - Passes ASTM E 2180, ASTM G21. Includes specially formulated antimicrobial.

Technical Data

Item Number: T18A2S, T18A2T


Product Description: A woven fabric using .018" diameter vinyl coated 500 denier polyester core yarns woven in the warp and fill.

Attribute	ASTM	Warp	Fill	Typical				
Construction, end/inch	D3775-12	36.0 ±0.5	26.0 ±0.5					
Weight, oz/yd²	D3776-09			17.8				
Weight, g/m ²	D3776-09			603.5				
Tensile Strength (grab), lbf / daN	D5034-09	569.8 /253.5	467.9 / 208.1					
Tensile Strength (strip), lbf / daN	D5035-11	314.9 / 140.1	224.1 / 99.7					
Tear Strength (trapezoidal), lbf / daN	D5733	87.6 / 39.0	57.4 / 25.5					
Elongation, %	D5035-11	32.3	24.9					
Abrasion Resistance (CS10/500 cycles/ with no added weight)	D3884-09		No Exposure of Core Yarn					
Flammability Rating			CA Title 19 & NFPA 701					
Weatherability, 1200 hours	G154		Trace Discoloration					
Mildew Resistance	G21-13		No growth					
Thickness, inches/mm	D1777-96		0.037"/0.9398 mm					
The above results are a representation of real data from single test samples. Presently no specification is incorporated.								


Profile	Total Solar		Visible		Insulating Glass				
Angle	Ts	Rs	As	Ts	Rs	As	1/2" Clr.	1" Clr.	1" HA
0	0.08	0.03	0.89	0.12	0.03	0.85	0.18	0.14	0.13
45	0.05	0.04	0.91	0.08	0.04	0.88	0.15	0.12	0.11

DISTRIBUTED OR MANUFACTURED BY:









Due to the technical limitations of digital cameras and inconsistencies of display monitors, the characteristics and colors of the fabrics seen on your screen may be slightly different than the actual product.

Galaxy Black T18A2S006 x 126"