

OMNOVA's *Underlining* is a plastisol coated, woven fabric designed for use under seat lining.

Industries & Markets

- Marine

End-Use Applications

- Coated Fabrics for Boats and Personal Watercraft

Physical Specifications

Weight (CFFA-700d)	10.4 oz/lin yd [7 oz/yd ²]
Weight, Metric (CFFA-700d)	295 g/lin m [198 g/m ²]
Width (CFFA-700a)	54 in. [137 cm]
Face Composition	PVC
Roll Size	100 lin yd [91 lin m]
Emboss Level	Light
Shipping Weight/ Roll	68 lb [31 kg]

Performance Features

Use	Indoor/Outdoor
QUV hours (minimum)	650
Tensile Strength #, min (CFFA-14)	100 Warp, 100 Fill
Tack Strength #, min (CFFA-14)	68 Warp, 68 Fill
Blocking (CFFA-4 No. 1)	Pass
W-Flex - 25,000 cycles (CFFA-10)	Pass
Crocking Resistance - 20 cycles no stain (CFFA-7)	Pass
Fungal Resistance (ASTM-G-21)	Pass
Cold Crack (CFFA-6a)	-20 °F [-29 °C]

Note: Due to possible variances in your computer monitor, the colors and patterns displayed may vary slightly from the actual product. Customers should always obtain and compare actual samples before specifying.



World Headquarters

OMNOVA Solutions Inc.
25435 Harvard Road
Beachwood, OH 44122-6201
USA
Phone: +1 216-682-7000
Email: upholstery@omnova.com

Thailand Manufacturing Plant

111/7 Moo 2, T. Nikompattana
Amphur Nikompattana
Rayong 21180, Thailand
Phone: +011-66-38-897103
Fax: +011-66-38-637749

**OMNOVA Decorative Products
(Shanghai) Co., Ltd**

Manufacturing and China
Headquarters
No. 469 Wenjin Road
Minhang District
Shanghai 200245, China
Phone: +011 (86-21) 6430-7800
Fax: +011 (86-21) 6430-6468

All OMNOVA products and services are offered and sold subject to the OMNOVA standard terms and conditions of sale agreement set forth at www.omnova.com

Trademarks are property of OMNOVA Solutions Inc. unless otherwise noted.